

AT A GLANCE

Manufacturer

SIB, Sociedade Industrial
De Britagem De Pedra, LDA

Nano Technology
Environmentally friendly
VOC and APEO-free

Water vapor permeable
Reduces surface abrasion
Indoor and outdoor use



DESCRIPTION:

SIB OIL 2K strengthen the the seal of Prosib 330 or Prosib +. SIB OIL 2K gives resistance and additional protection and enhance the colour on SIB Extreme Style, SIB Extreme Flow and Trowel.

SIB OIL 2K is a newest generation product which color enhance overlay and protects it in one layer. The combination of the oil (A) and the accelerator (B) guarantees a quick drying. Can also be applied as renovation and maintenance oil on surfaces which are treated with Prosib 330 or Prosib +.

Applied in only on layer

Can be pigmented to enhance white or dark colours

- Enhances the natural look and feel of overlay or terrazzo
- Environmentally friendly: 0% VOC!
- Does not contain any water or solvents
- Easy to maintain
- No overlaps or starting marks
- Durable protection
- Minimal use: 60 - 120 m²/L
- Wear-resistant
- Water-resistant, ideal for kitchens and bathrooms
- Heat-resistant
- Very fast curing: 80% in 2 days
- After 5 days, the surface can be cleaned with water and soap

TECHNICAL PROPERTIES AND CHARACTERISTICS

| | |
|-------------------------|---|
| Physical state at 20°C | Liquid |
| Odour | A Component: Oily B Component: None |
| Flash Point | A Component: 99°C B Component: 160 °C |
| Density | B Component 0.90 g/cm ³ |
| VOC Content | 0 g/l |
| Application temperature | Min. +5 °C, max. +55 °C |
| Consumption: | 60-120 m ² /L in 1 application |

APPLICATION INFORMATION:

Since SIB OIL 2K is applied as a top sealer on Prosib 330 and Prosib + surface preparation is done. If the surface has become dirty or dusty it should be cleaned with a scrubber drier and left to dry.

Carefully mix the two components (1 to 2 minutes).

Once the cleaned surface is dry, spread out a small quantity of SIB OIL 2K (cloth or polishing machine with thin white pad). Work in zones of 5 - 10 m².

Let absorb during a few minutes. Thoroughly remove all excess of oil (cloth or polishing machine with white pad) within 15 minutes per zone. The surface should feel dry! Finish all zones the same way.

In a well ventilated room, the surface can be used 24 - 36 hours after the application.

After 5 days the floors can be washed with PH neutral soaps.

› Tips & tricks

- The product may NOT be diluted!
- Stir the product well before application. When using several containers at one site, it is recommended to mix them for an even result.

SIB OIL 2K

Versatil Sealer

MAY 2019

ATTENTION:

Cloths, saturated with oil, may spontaneously combust. After usage, they need to be soaked in water before disposal.

CONSUMPTION:

60 - 120 m²/L, depending on the floor finish. SIB OIL 2K may be used for a maximum of 4 - 6 hours after mixing.

It is always recommended to make a sample in order to calculate the exact usage.

PRODUCTION, PACKAGING, STORAGE, SAFETY AND VALIDITY

Combined can of 1,3 L: 1 L SIB OIL 2K (A) and 0,3 L SIB OIL 2K Accelerator (B)

Combined can of 3,5 L: 2,750 L SIB OIL 2K (A) and 0,750 L SIB OIL 2K Accelerator (B)

The product can be stored up to 36 months in dry conditions and in its original packaging. Keep away from frost and store at stable temperatures.

Safety and Health:

Use adequate PPE: waterproof gloves boots and goggles.

Avoid contact with skin and eyes; prolonged contact may cause skin irritation.

Do not drink, eat or smoke while handling the product.

Non flammable and non-explosive product.

See the complete product MSDS.

LIMITED WARRANTY:

SIB, Sociedade Industrial De Britagem De Pedra, LDA warrants its materials to be of good quality and, at its option, will replace or refund the purchase price of any material proven to be defective within one (1) year from date of purchase. The above remedies shall be the limit of SIB's responsibility. Except for the foregoing, all warranties expressed or implied, including merchantability and fitness for a particular purpose, are excluded. SIB shall not be liable for any consequential, incidental, or special damages arising directly or indirectly from the use of the materials.